## CHOICE® ALUMINIZED FABRICS 11HT26-AL7

A Norfab light/medium weight fabric of Aramid fiber blend with fiberglass core yarn, aluminized 1 side. Applications include safety clothing, gloves, mitts, jackets, curtains, and other industrial applications. Resistant to heat sources, offers excellent thermal protection for safety garments.

## **About NOR\*FAB Corporation**

NOR\*FAB manufactures textile products using flame resistant synthetic fibers suited for use at high temperatures and for personal protection. These items include broad woven roll goods and narrow products in the form of woven and knitted tapes, sleeving, rope, and gasketing. NOR\*FAB uses para-aramid, meta-aramid, melamine, phenolic, oxidized PAN, flame resistant rayon, polybenzimideazole, and other technical fibers blended into unique yarns which provide high levels of heat protection and insulation.

NOR\*FAB produces many of these yarns on the DREF Spinning System for use in the weaving, knitting, gasket, and wire & cable industries. NOR\*FAB possesses the largest collection of DREF III spinning frames of any yarn manufacturer in the world.

## Among its offerings, NOR\*FAB boasts fabric lines for the following end uses:

Firefighting

OMNI Vantage<sup>™</sup>, OMNI Elite®, OMNI 45<sup>™</sup>, and OMNI Quilt<sup>™</sup>

**Electric Arc Protection** 

NF Arc™, ArcWeld®

**Welding Protection** 

ArcWeld®

**Cut Protection** 

CutPro®

**Molten Metal Splash Protection** 

Choice®

## **Since 1979**

Proud American Manufacturers of Flame Resistant Textiles



NORFAB AL7 Aluminized Fabric Data Sheet	
Style	11HT26-AL7
Base Fabric	Aramid cover with fiberglass insert
Color/Appearance	Yellow, Aluminized 1 side
Style	Herringbone Twill
Fabric Weight (oz/yd², average)	14 (475 gm/m²)
Fabric Thickness, (in)	0.035
Warp Strength (lbs) (1" unraveled)	163
Fill Strength (lbs) (1" unraveled)	250
Flammability- After Flame (Seconds)	0.0
Flammability- Char Length (inches)	0.0
Adhesion after Wet Flex	Pass
Reflectivity after Abrasion (seconds) (ASTM F1939)	28
RPP Rating (cal/cm²)	55
Taber Abrasion	1100
Molten Iron Splash (ASTM F955)	Pass
Molten Aluminum Splash (ASTM F955)	Pass
Other Certifications	ISO 11612-2015 A1, A2, B1, C3, D1, E3, F2

All data +/- 10%.



1310 Stanbridge Street,
Box 830, Norristown, PA 19404-0830 U.S.A.
Tel: 610-275-7270 • 800-441-9680 • Fax: 610-277-6106
Email: sales@norfab.com • www.norfab.com