

Industrial Gaskets



INDUSTRIAL GASKETS

MATERIALS

Tetraglas® - Type E Fiberglass

Tetraglas® - Type E Fiberglass with PTFE coating

Tetraglas® - Type E Fiberglass with Vermiculite coating

Tetraglas® - Type E Fiberglass with Reflective Foils

Tetraglas® - Type E Fiberglass with Silicone Coating and Impregnation

Tetraglas-T® - Type E Fiberglass with Rubber Coating

Tetraglas 3000®- Amorphous Silica

Tetraglas 3000®- Amorphous Silica with Silicone Coating

Ceramic Fiber - Woven, Paper

DARPAC®- Compressed Non-Asbestos

Tetrablue® - Felted Non-Asbestos

Type 304 Stainless Steel core for tadpole gaskets

Inconel Mesh core for tadpole gaskets

PTFE – Envelope Gaskets, Sheets, Coating Expanded PTFE – Gaskets, Sheets

Graphite - Gaskets, Sheets, Coating

Graphite – Gaskets, Sneets, Coatii

Rubber - Gaskets, Sheets

Needled Blankets

Spirotallic Spiral Wound Gaskets

AVAILABLE CONSTRUCTION OPTIONS

Custom Combinations
Flange Type – Ring, Full Face, Elliptical, Obround
Folded and Stitched
Solid Cut
Handhole & Manhole
Luting and Groove Packing
PTFE Envelope with Fillers
Tadpole
Spiral Wound

Darco Southern continues to be a premier manufacturer of industrial gasket products since 1976. Darco Southern provides high temperature thermal and protective sealing solutions globally. Our gasket products are used a variety of applications including commercial and industrial boilers and furnaces, chemical processing, petroleum refining, power generation, metal processing and more.

There are a number of variables that need to be considered to ensure proper gasket selection. Our vast array of available materials combined with our vertically integrated, in-house product design, engineering and manufacturing capabilities allow us to design, prototype and produce the optimal solution, in a minimal timeframe. Although Darco offers "standard" gasket product configurations, we welcome the opportunity to develop a custom gasket around your design requirements.

Ask us about the Darco Southern 4D Process!

MAXIMUM CONTINUOUS TEMPERATURE

Tetraglas® - 1000°F (540°C)

Tetraglas® with PTFE - 500°F (260°C)

Tetraglas® with Vermiculite - 1500°F (815°C)

Tetraglas® - Type E Fiberglass with reflective foils - 500°F (260°C)

Tetraglas® - Type E Fiberglass with silicone coating and impregnation - 500°F (260°C)

Tetraglas-T® - Type E Fiberglass with rubber coating - 500°F (260°C)

Tetraglas® with Graphite - 1000°F (540°C)

Tetraglas3000® - 1800°F (980°C)

Tetraglas3000® with silicone coating - 500°F (260°C)

Ceramic - 2300°F (1260°C)

DARPAC®- 450°F (232°C) & 700°F (370°C)

Graphite – Oxidizing environment (such as air): -400°F (-240°C) to 950°F (510°C). Mild Oxidizing environment of most gasket applications: -400°F (-240°C) to 1500°F (850°C).

Non-Oxidizing environment: Up to the limit of the stainless steel 1800°F (980°C).

Graphite limit is 5400°F (2980°C).

PTFE - 500°F (260°C)

Rubber - up to 500°F (260°C)

SIZE RANGE

Industry Standard Custom



