

NF ARC

A Norfab woven 7 oz/yd² "light weight" dimensionally stable fabric blend of Para-Aramid, OPF, and Novoloid (Phenolic) fibers. Excellent for Electric Arc Protective garments; when used as a single layer, will meet 8 Cal requirements.

- 100% inherent flame resistance that will never wash out or wear out



About NOR*FAB Corporation

NOR*FAB manufactures textile products using flame resistant synthetic fibers suited for use at high temperatures and for personal protection. These items include broad woven roll goods and narrow products in the form of woven and knitted tapes, sleeving, rope, and gasketing. NOR*FAB uses para-aramid, meta-aramid, melamine, phenolic, oxidized PAN, flame resistant rayon, polybenzimidazole, and other technical fibers blended into unique yarns which provide high levels of heat protection and insulation.

NOR*FAB produces many of these yarns on the DREF Spinning System for use in the weaving, knitting, gasket, and wire & cable industries. NOR*FAB possesses the largest collection of DREF III spinning frames of any yarn manufacturer in the world.

Among its offerings, NOR*FAB boasts fabric lines for the following end uses:

Firefighting

OMNI Vantage™, OMNI Elite®, OMNI 45™, and OMNI Quilt™

Electric Arc Protection

NF Arc™, ArcWeld®

Welding Protection

ArcWeld®

Cut Protection

CutPro®

Since 1979

Proud American Manufacturers of Flame Resistant Textiles



NF Arc Data Sheet

Fabric Style	07PT349-62
Specifications	Complies with and Exceeds NFPA 70E*
Base Fabric	Para-Aramid, OPF, Novoloid (Phenolic)
Available Colors	Light Green
Weave Style	Plain Weave
Fabric Weight oz./yd ² (g/m ²)	7.0 (230)
Fabric Thickness inches (mm)	0.019 (0.48)
Warp Strength grab method, lbs (kg)	220 (99)
Fill Strength grab method, lbs (kg).	175 (79)
Trapezoidal Tear Strength lbs. (kg), warp x fill	20 x 12 (9 x 5.5 kg)
Arc Thermal Performance Value (ATPV) cal./cm ²	ATPV 8.1 (sgl layer)
Heat Attenuation Factor (HAF)	67.7%
Heat, Char Resistance	Passes
NFPA 70E	Level 2
Fabric Finish Number	62-Water Softened
Specify Order	Example: 07PT349-60"-62

* Testing conducted by Kinetrics Inc, Canada to ASTM F1959/F1959M-04.

All data intended as general information and no warranties, guarantees, or claims of fitness for use are expressed or implied by NOR*FAB Corp.



1310 Stanbridge Street,
Box 830, Norristown, PA 19404-0830 U.S.A.
Tel: 610-275-7270 • 800-441-9680 • Fax: 610-277-6106
Email: sales@norfab.com • www.norfab.com