

# CHOICE® ALUMINIZED FABRIC

*05WKRS10-60-AL8*

A Norfab light weight rip-stop warp knit fabric of 100% Para-Aramid, aluminized one side.

The principal application is Proximity Fire Fighting. Excellent for radiant heat.

## About NOR\*FAB Corporation

NOR\*FAB manufactures textile products using flame resistant synthetic fibers suited for use at high temperatures and for personal protection. These items include broad woven roll goods and narrow products in the form of woven and knitted tapes, sleeving, rope, and gasketing. NOR\*FAB uses para-aramid, meta-aramid, melamine, phenolic, oxidized PAN, flame resistant rayon, polybenzimidazole, and other technical fibers blended into unique yarns which provide high levels of heat protection and insulation.

NOR\*FAB produces many of these yarns on the DREF Spinning System for use in the weaving, knitting, gasket, and wire & cable industries. NOR\*FAB possesses the largest collection of DREF III spinning frames of any yarn manufacturer in the world.

**Among its offerings, NOR\*FAB boasts fabric lines for the following end uses:**

### **Firefighting**

OMNI Vantage™, OMNI Elite®, OMNI 45™, and OMNI Quilt™

### **Electric Arc Protection**

NF Arc™, ArcWeld®

### **Welding Protection**

ArcWeld®

### **Cut Protection**

CutPro®

### **Molten Metal Splash Protection**

Choice®

**Since 1979**

*Proud American Manufacturers of Flame Resistant Textiles*



## NORFAB AL8 Aluminized Fabric Data Sheet

<b>Style</b>	<b>05WKRS10-60-AL8</b>	
<b>Base Fabric</b>	<b>100% Para-Aramid</b>	
<b>Color/Appearance</b>	Yellow, Aluminized 1 side	
<b>Style</b>	Rip Stop Knit Fabric	
<b>Fabric Weight</b> (oz/yd <sup>2</sup> , average)	ASTM D3776	7.6 (256 g/m <sup>2</sup> )
<b>Fabric Thickness</b> , (in)	ASTM D1777	0.026
<b>Fabric Width</b> , (in)	60 (1.52 m)	
<b>Trap Tear- Courses</b> (lbs)	ASTM D5587	40 (178 N)
<b>Trap Tear -Wales</b> (lbs)	ASTM D5587	42 (186 N)
<b>Grab Break- Courses</b> (lbs)	ISO 13934-1	144 (640 N)
<b>Grab Break- Wales</b> (lbs)	ISO 13934-1	142 (630 N)
<b>Flammability-</b> After Flame (seconds)	ASTM D6413	0.9
<b>Flammability-</b> Char length (inches)	ASTM D6413	0
<b>Adhesion after Wet Flex</b>	NFPA 1971	Pass
<b>Reflectivity after Abrasion</b> (Seconds) (ASTM F1939)	NFPA 1971	45
<b>RPP Rating</b> (cal/cm <sup>2</sup> )	90	
<b>Certified to ISO 11612</b>	2015 Edition	A1, A2, B1, C4, E3, F2
<b>Molten Iron Splash</b>	ASTM F955	PENDING
<b>Molten Aluminum Splash</b>	ASTM F955	PENDING

All data +/- 10%. All data intended as general information and no warranties, guarantees, or claims of fitness for use are expressed or implied by NOR\*FAB Corp.



1310 Stanbridge Street,

Box 830, Norristown, PA 19404-0830 U.S.A.

Tel: 610-275-7270 • 800-441-9680 • Fax: 610-277-6106

Email: sales@norfab.com • www.norfab.com